

#### Product description

Ultramid® A 205F Black 651 is an unreinforced polyamide 66 for injection moulding. This grade offers two main advantages: excellent filling qualities and UL 94 V2 under 0.4 mm. It is particularly suitable for the moulding of long parts with thin wall sections

#### Injection Notes

The material is supplied in airtight bags, ready for use. In case that the virgin material has absorbed moisture, it must be dried with a dehumidified air drying equipment, dew point mini -20°C. Recommended time 2-4h.

Injection Advice:

- For unfilled polyamides, BASF SE recommends the use of high alloy steel with a low chromium content. For example: X38CrMoV5-1 (EN Norm) - 1.2367 / 1.2343 (DIN Norm). In the case of high requirements on surface quality a mould temperature of up to 120°C can be considered.
- The processing parameters like processing temperatures are a recommendation and can be adjusted in function of injection machine size, part geometry / design.

#### Disclaimer

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and it is in no way binding. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. ANY WARRANTY OF PRODUCT PERFORMANCE, MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE IS EXPRESSLY EXCLUDED. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorizations. Users are requested to check that they are in possession of the latest version of this document, and BASF SE is at their disposal to supply any additional information.

#### Safety Information

Detailed information regarding safety are available on the safety data sheet (MSDS). MSDS is sent with the first material order or available by contacting our customer services

#### Regulations Compliance

This product is not intended to be used for the following regulated market: food contact, drinking water, toys, cosmetics or medical devices.

This grade complies with RoHS Directive 2011/65/EU, 2015/863 and local regulations as amended.

#### Customer Services

Our customer services are not only concerned with manufacturing and supply of Engineering Plastics products. We are available to assist our customers in finding technical solutions that meet their requirements. Specific support is in particular offered on:

- Material selection
- Material testing
- Parts design advice, training for design engineers
- Part testing
- Design simulation
- Processing through different technologies
- Assembly and post-processing technology expertise
- Parts optimization through Computer Aided Design

## Product Information

Typical values for uncoloured product at 23 °C <sup>1)</sup>	Test method	Unit	Values <sup>2)</sup>
<b>General Properties</b>			
South and Central America	-	-	+
Processing: Injection moulding (M), Extrusion (E), Blow moulding (B)	-	-	M
Colour: black (bk), uncoloured (un), coloured (co), transparent (tr)	-	-	bk,un,co
Pellets	-	-	+
<b>Physical</b>			
Water absorption, 24 h in water, 23 °C	ISO 62	%	1.5
Moisture absorption, equilibrium 23°C/50% r.h	similar to ISO 62	%	3.00
Density	ISO 1183	kg/m <sup>3</sup>	1140 / -
<b>Mechanical properties</b>			
			dry / cond.
Tensile modulus	ISO 527-1/-2	MPa	3200 / 1400
Yield stress, 50 mm/min	ISO 527-1/-2	MPa	80 / 50
Tensile stress at yield, 2 in/min (ASTM)	ASTM D 638	MPa	80 / -
Stress at break	ISO 527-1/-2	MPa	70 / 45
Yield strain, 50 mm/min	ISO 527-1/-2	%	4 / 10
Strain at break	ISO 527-1/-2	%	30 / > 100
Tensile elongation at break, 2 in/min (ASTM)	ASTM D 638	%	25 / -
Flexural modulus	ISO 178	MPa	3000 / 1500
Flexural modulus (ASTM)	ASTM D 790	MPa	3350 / -
Flexural strength	ISO 178	MPa	110 / 50
Flexural strength (ASTM)	ASTM D 790	MPa	125 / -
Charpy notched impact strength ISO 179/1eA (23°C)	ISO 179/1eA	kJ/m <sup>2</sup>	5 / 10
Charpy impact strength ISO 179-1eU (23°C)	ISO 179/1eU	kJ/m <sup>2</sup>	N / N
Izod notched impact strength ISO 180/A (23°C)	ISO 180/A	kJ/m <sup>2</sup>	5 / 10
Izod impact strength ISO 180/U (23°C), MPTS	ISO 180/U	kJ/m <sup>2</sup>	N / N
Izod impact strength (area) ASTM D 256 (23 °C)	ASTM D 256	MPa	45 / N
<b>Thermal properties</b>			
HDT B (0.45 MPa)	ISO 75-1/-2	°C	205
HDT A (1.80 MPa)	ISO 75-1/-2	°C	65
Melting temperature, DSC (10°C/min)	ISO 11357-1/-3	°C	263
<b>Electrical properties</b>			
			dry / cond.
Surface resistivity	IEC 62631-3-2	Ohm	5E15 / 1E14
Volume resistivity	IEC 62631-3-1	Ohm*m	1E13 / 1E13
Electric strength (d = 0.8 mm)	IEC 60243-1	kV/mm	35 / -
Electric strength (d = 2.0 mm)	IEC 60243-1	kV/mm	22 / -
Relative permittivity (1 MHz)	IEC 62631-2-1	-	3.5 / -
Dissipation factor (1 MHz)	IEC 62631-2-1	E-4	0.033 / -
Comparative tracking index, CTI, test liquid A	IEC 60112	-	600 / 600
Comparative tracking index, CTI M, test liquid B	IEC 60112	-	550 / -
<b>Flammability</b>			
Burning Behav. at 1.6 mm nom. thickn.	IEC 60695-11-10	class	V-2
Burning Behav. at thickness 0.4 mm	IEC 60695-11-10	class	V-2
Burning Behav. at thickness 0.8 mm	UL-94, IEC 60695	class	V-2
Glow Wire Flammability Index (1.6 mm)	IEC 60695-2-12	°C	800
Oxygen index	ISO 4589-1/-2	%	29
<b>Injection</b>			
Pre/Post-processing, Pre-drying, Temperature	-	°C	80
Pre/Post-processing, max. allowed water content	-	%	0.2
Injection molding cylinder temperature 1 (feed zone)	-	°C	265 - 275
Injection molding cylinder temperature 2 (compression)	-	°C	270 - 280
Injection molding cylinder temperature 3 (metering-zone, head room of screw)	-	°C	280 - 285
injection molding, Mold temperature, range	ISO 294	°C	60 - 80

### Footnotes

1) If product name or properties don't state otherwise.

2) The asterisk symbol "\*" signifies inapplicable properties.

BASF SE

67056 Ludwigshafen, Germany